

wherein the polyester polyol (a) is a branched structure having a calculated molecular mass from 600 to 1400, an acid value from 0 to 30 mg KOH/g and a hydroxyl value from 250 to 600 mg KOH/g with a calculated hydroxyl functionality from 4.5 to 10, and is composed of randomly positioned components consisting of

- AA
- (a1) hydroxyl components comprising 0 wt-% to 20 wt-% of at least one diol and 80 wt-% to 100 wt-% of at least one polyol having 3 to 6 hydroxyl groups,
 - (a2) carboxyl components comprising 0 wt-% to 20 wt-% of at least one monocarboxylic acid and 80 wt-% to 100 wt-% of at least one dicarboxylic acid, and optionally
 - (a3) at least one hydroxycarboxylic acid component,
- the sum of the percentages by weight of components (a) to (c), of components (a1) and of components (a2) being 100% in each case.

Please ADD new claim 11 as follows:

Claim 11. Coating agents with resin solids comprising

- A2
- (a) 10 wt-% to 80 wt-% of a non-aromatic polyester polyol,
 - (b) 0 wt-% to 70 wt-% of at least one constituent selected from the group consisting of hydroxyl-functional binders that are different from polyester polyol (a), hydroxyl-functional reactive thinners and combinations thereof, and
 - (c) 20 wt-% to 60 wt-% of at least one cross-linking agent for the hydroxyl-functional components (a) and (b),

wherein the polyester polyol (a) has a calculated molecular mass from 600 to 1400, an acid value from 0 to 30 mg KOH/g and an hydroxyl value from 250 to 600 mg KOH/g with a calculated hydroxyl functionality from 4.5 to 10, and is composed of components which comprise

- (a1) hydroxyl components comprising 0 wt-% to 20 wt-% of at least one diol and 80 wt-% to 100 wt-% of at least one polyol having 3 to 6 hydroxyl groups,
- (a2) carboxyl components comprising 0 wt-% to 20 wt-% of at least one monocarboxylic acid and 80 wt-% to 100 wt-% of at least two